

VSG-WM280/FW12



Material description: This material is developed for high performance applications at temperatures up to 1100°C and high mechanical load. Very thin walled 3 D-components can be produced where extremely light weight structures are needed.

		Value	Unit	Standard
Manufacturer		Walter E.C. Pritzkow Spezialkeramik		
Textile	Fibre	M99 (1800 Denier)		
	Fibre manufacturer	Vulcan Shield Global		
	Fabric type	WM-280		
	Layer thickness	0,2	mm	
	Preform structure	Anisotropic fabric 0/90, isotropic possible		
	Fibre volume content	39		
Matrix composition		85% Al ₂ O ₃ ; 15% 3YSZ		
Production process		open laminated, hand laminate, press moulds		
Maximum manufacturable component size		4	m	
Minimum wall thickness		0,2	mm	
Joining process		Yes		
Coatability		Yes		
Temperatures	Recommended continuous operating temperature without mechanical load	< 1.300	°C	
	Recommended continuous operating temperature under mechanical load	< 1.200	°C	
	Recommended continuous operating temperature under high mechanical load	< 1.000	°C	
Machineability		Yes, certain diamond-coated cutting edges, laser		
TRL		5 - 9		
Density		2,6	g/cm ³	DIN EN 1389
Porosity		30	%	DIN EN 1389
CTE	@+300	-	10 ⁻⁶ 1/K	DIN EN 1159-1
	@+600	-	10 ⁻⁶ 1/K	DIN EN 1159-1
	@+900	-	10 ⁻⁶ 1/K	DIN EN 1159-1
	@+1100	-	10 ⁻⁶ 1/K	DIN EN 1159-1
λ	@+300	-	W/(mK)	DIN EN 1159-2
	@+600	-	W/(mK)	DIN EN 1159-2
	@+900	-	W/(mK)	DIN EN 1159-2
	@+1100	-	W/(mK)	DIN EN 1159-2
Strength	Bending anisotropic 0/90° at RT	307	MPa	DIN EN 658-3 3PB
	Bending anisotropic +/-45° at RT	93	MPa	DIN EN 658-3 3PB
	Shear 0/90° at RT	15	MPa	DIN EN 658-4
	Tensile anisotropic 0/90° at RT	212	MPa	DIN EN 658-1
	Tensile anisotropic +/-45° at RT	87	MPa	DIN EN 658-1
	Tensile 0/90°at 1100 °C	145,2	MPa	DIN EN 658-1
	Tensile 0/90°at 1200°C	138	MPa	DIN EN 658-1
	Compression 0/90°at RT	-	MPa	DIN EN 658-2
Young' s Modulus	Bending 0/90°at RT	93	MPa	DIN EN 658-3
	tension 0/90°at RT	96	MPa	DIN EN 658-1
	compression 0°/90° at RT	123	MPa	DIN EN 658-2
Emissivity		available		